

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



5

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 :
C12P 7/62 // (C12P 7/62, C12R 1:05)

A1

(11) International Publication Number: WO 96/25509

(43) International Publication Date: 22 August 1996 (22.08.96)

(21) International Application Number: PCT/GB96/00293

(22) International Filing Date: 9 February 1996 (09.02.96)

(30) Priority Data:
9503174.6 17 February 1995 (17.02.95) GB

(71) Applicant (for all designated States except US): ZENECA LIMITED [GB/GB]; 15 Stanhope Gate, London W1Y 6LN (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): NAYLOR, Linda, Anne [GB/GB]; 2 The Court Yard, Trafford Hill, Aislaby, Eaglescliffe, Cleveland TS16 0Q2 (GB). WOOD, John, Christopher [GB/GB]; 58 Berwick Chase, Oakerside Park, Peterlee, Co. Durham SR8 1NQ (GB).

(74) Agents: LOCKE, Timothy, John; Zeneca Bioproducts, Intellectual Property Group, P.O. Box 2, Belasis Avenue, Billingham, Cleveland TS23 1YN (GB) et al.

(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KG, KZ, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).

Published

With international search report.

(54) Title: PROCESS FOR THE MICROBIOLOGICAL PRODUCTION OF PHA-POLYMERS

(57) Abstract

A process for producing poly-3-hydroxyalkanoate (PHA) by culturing *Alcaligenes* on a low water-solubility aliphatic carboxylic acid and/or hydrolysable derivative of low solubility in pure water, by fermenting the organism in a growth step on a nutrient medium containing *inter alia* phosphorus in a quantity corresponding to the intended quantity of bacterial cells to be grown until cell growth stops or slows substantially, then in a PHA accumulation stage fermenting the grown cells by feeding said low-solubility carbon source while monitoring pH and adjusting it by addition of ammonia and/or alkaline alkali metal compound until a design quantity of PHA has been produced, and recovering PHA from the product. Further phosphorus may be fed to the accumulation stage at a rate sufficient to permit some bacterial growth but insufficient to permit growth to the exclusion of PHA accumulation. The over-all carbon (as C) to phosphorus (as P) weight ratio is typically in the range 40-100 in the growth stage and 300 to 600 in the accumulation stage.

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

Process for the microbiological production of PHA-polymers

THIS INVENTION relates to polymer production and in particular to a process for microbiologically producing poly-3-hydroxyalkanoate (PHA) from a fatty carbon source.

5 According to EP-A-520405 such a PHA containing 3-hydroxybutyrate (HB) repeating units can be made by culturing, possibly under nitrogen and phosphorus limitation, a strain belonging to the genus Alcaligenes
10 lipolytica (FERM BP-3819) on a C₁₀-C₂₂ fatty acid or derivative thereof; however, other Alcaligenes (specifically A. eutrophus and A. latus) are reported to be incapable of growth on such feedstock, or at best capable of only extremely slow growth.

According to Eggink et al (Industrial Crops and
15 Products 1993, 1, 157-163) such PHA can be made by culturing A. eutrophus on oleic acid, the yield of PHA being greater under nitrogen limitation.

We have now discovered fermentation conditions in which Alcaligenes will produce PHA at high yields and/or
20 output rates from aliphatic carboxylic acid or derivatives hydrolysable thereto as carbon source.

According to the invention a process for producing PHA comprises culturing at least one strain of Alcaligenes on a carbon source comprising at least one
25 aliphatic carboxylic acid and/or derivative thereof hydrolysable thereto said acid or derivative or mixture thereof being of low solubility in pure water, by the steps of:

- 30 (a) providing a body of nutrient medium containing assimilable compounds of nitrogen, phosphorus,

sulphur and trace elements, the phosphorus quantity corresponding to the requirement of the intended quantity of bacterial cells to be grown;

(b) inoculating the body with viable cells of

5 Alcaligenes;

(c) providing in said body a quantity of assimilable carbon compound at least corresponding to the quantity of bacterial cells to be grown;

(d) aerobically fermenting the inoculated body while
10 monitoring pH and adjusting it by addition of ammonia and/or alkaline alkali metal compound until cell growth stops or slows substantially;

(e) aerobically fermenting the product of step (d) by feeding said low-solubility carbon source while
15 monitoring pH and adjusting it by addition of ammonia and/or alkaline alkali metal compound, until a design quantity of PHA has been produced; and

(f) recovering PHA from the product of step (e).

20 The carbon compound provided in step (c) can be any that the Alcaligenes can assimilate. Thus it can be for example a sugar, a sugar alcohol, a sugar acid or an alkanol or alkanolic acid. Conveniently it is an aliphatic acid or derivative hydrolysable thereto, for example, the same as is to be used in step (e).

25 In step (d) cell growth stops or slows substantially when the phosphorus provided in step (a) has been exhausted, typically to less than 10 mg P per litre of supernatant. The assimilable carbon compound is normally fed gradually so as to avoid exceeding the provision of
30 oxygen for the aerobic fermentation and (where

appropriate) to avoid a toxic concentration of such compound. The over-all carbon (as C) to phosphorus (as P) weight ratio in this step is typically in the range 40-100, especially 50-80, differing according to the chemical composition of the compound.

In step (e) and possibly step (c) the aliphatic acid whether used as such or as a hydrolysable derivative, is preferably less than 3; especially less than 1, % w/w soluble in pure water at ambient temperature. Typically it contains one or more alkyl groups containing 8-25, especially 10-22 carbon atoms. Preferably the derivative is an ester, conveniently a triglyceride, especially a naturally occurring triglyceride. The fatty acid may be saturated (provided this does not lead to a melting point higher than the temperature of steps (d) and (e)) or mono- or poly-unsaturated. Examples of triglycerides are animal products such as butter, whale oil, beef tallow, pork fat, mutton fat; fish oils; and vegetable oils such as olive oil, corn oil, rapeseed oil, castor oil, soya oil, sunflower oil and linseed oil. As-extracted unsaturated oils can be partly or wholly hydrogenated. It appears that such triglycerides need not be refined to human food standard : among the impurities tolerated or productively assimilated are the corresponding free acids, phospholipids and traces of coloured materials such as trace metal compounds and chlorophyll. As alternative or additional ester there may be used mono- or di-glycerides, or mono-ester derivatives of the fatty acids such as the methyl esters proposed for use as "bio-diesel". A mixture of derivatives can be used, especially if the carbon source includes material melting

at above fermentation temperature.

If the aliphatic acid contains an even number of carbon atoms and is the sole carbon source in step (e) the product PHA is substantially or wholly polyhydroxybutyrate (PHB) homopolymer. If polyhydroxybutyrate/-valerate copolymer (PHBV) is required, there should be present a carbon source containing an odd number of carbon atoms; this may be part or all of the aliphatic acid (derivative) or may be additional thereto, for example propionic acid or n-propyl alcohol. The product PHA preferably contains up to 30 mol % of V, especially 3-25 mol % V, balance B.

The process can use any species or strain of Alcaligenes. Specific examples are A. eutrophus, A. latus, A. faecalis, A. ruhlandii, A. aquamarinus, A. lipolytica. It is an especial advantage of the process that bacteria other than A. lipolytica appear to be at least as active and efficient as A. lipolytica, which was until this invention believed to be uniquely capable of converting fatty acid esters to PHA.

The cell dry-weight at the end of step (e) or in the steady state of that step if operating continuously is preferably in the range 100-400 g/litre. The design quantity of PHA preferably corresponds to a PHA content in the range 60-80% w/w on cell dry weight (including PHA).

In a preferred form of the process phosphorus is fed to step (e) at a rate sufficient to permit some bacterial growth but insufficient to permit maximum growth, that is, growth to the exclusion of PHA accumulation or growth to the maximum available extent alongside accumulation.

(The latter applies to those species of Alcaligenes capable of simultaneous growth and accumulation).

Typically the weight ratio of total carbon (as C) to total phosphorus (as P) fed to step (c) is in the range 300 to 600. This appears to give a high output of PHA in a fed batch fermentation in virtue not only of the increased number of PHA-bearing cells and of the high PHA content of the cells, but also of faster reaction and high propionate efficiency. The phosphorus feed, conveniently as phosphate, is at a steady rate during the fermentation and preferably is at a fixed proportion of the carbon feed.

For step (e) the feeds, in addition to carbon source and (if any) said phosphorus compound, may include also other essential nutrients such as nitrogen, sulphur and trace elements, supplementing those present after step (d).

Step (e), and also step (d) if an oily carbon source of low water solubility is used, are carried out preferably with vigorous agitation at least by air-sparging and possibly also mechanically, so as to maximise the active surface area of the oil.

The pH in the growth (d) and accumulation (e) steps is preferably kept within half a pH unit of the value for most rapid reaction. Typically the pH is between 6.0 and 7.5, measured in the broth at fermentation temperature. Conveniently the addition of aqueous ammonia or the alkaline alkali metal compound is effected automatically in response to pH measurement by glass electrode.

The temperature in steps (d) and (e) can be as normally used for Alcaligenes using water-soluble carbon

sources, for example in the range 20-40°C, especially 28-38°C.

The product PHA is R-stereospecific and typically consists of 3-hydroxybutyrate repeating units alone ("PHB") or with 3-hydroxyvalerate units ("PHBV"), present at up to 30, especially 3-25, mol percent. The molecular weight of the PHA is for example over 50000, especially over 100000, and up to eg 2×10^6 .

Recovery of PHA in step (f) can be by any convenient method. In one general method the PHA-bearing cells are separated from the fermentation liquid by centrifugation, the cells are broken mechanically or chemically and the PHA is extracted in a solvent such as a halogenated hydrocarbon or an alkylene carbonate. In another the non-PHA cell material is solubilised by some or all of mechanical action, heat-shock, enzyme attack, surfactant attack and oxidation, leaving PHA particles as laid down in the cells or agglomerates of such particles. Such particles or agglomerates may be recovered dry, for use in melt-processing or solvent-processing, or as a latex for use as a coating or adhesive or for later conversion to dry PHA.

The following Examples show the production of PHBVs having a similar V content (ranges 6.9-8.7 mol %).

EXAMPLE 1

A stirred air-sparged laboratory fermenter of 15 litres capacity was charged with 8 litres of a medium containing per litre the following components:

3.00 g	Rape Seed Oil
0.93 ml	Conc H_3PO_4 (400 mg/l P)
2.18 g	$MgSO_4 \cdot 7H_2O$

7

1.81 g $(\text{NH}_4)_2\text{SO}_4$
2.18 g K_2SO_4
0.36 g Ca acetate
0.14 g $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$
5 0.09 g Na_2SO_4
0.04 g $\text{MnSO}_4 \cdot \text{H}_2\text{O}$
0.09 g $\text{ZnSO}_4 \cdot 7\text{H}_2\text{O}$
4.50 mg $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$

The pH was controlled at 6.8 by addition of 7M NH_4OH
10 and the temperature at 34°C.

200 ml (0.2 g of viable cells) of a culture of
Alcaligenes eutrophus (NCIMB 40124) were then stirred in.
The air flow rate was adjusted to maintain a dissolved
oxygen tension above 10% of air saturation at 1 bar
15 pressure absolute. Further rape seed oil was fed to
achieve an average oil uptake rate of up to 0.13g per g
of non-PHA cell mass per hour.

After 20h it was noted that the rate of oil uptake
decreased substantially, marking the substantial
20 exhaustion of phosphorus. At this point the weight ratio
of total carbon fed (as c) to total phosphorus fed (as P)
was 60. Thereafter rape seed oil and propionic acid were
fed until the uptake rate of those carbon sources became
slow, showing that further conversion to PHA was not
25 longer practical.

The resulting biomass was sampled and analysed for
cell dry weight, PHA content and PHA valerate content.

EXAMPLE 2

The procedure of Example 1 was repeated with the
30 modification that phosphoric acid was fed with the oil to
the fermenter during the PHA accumulation step to the

extent of 17% of total phosphorus used, keeping the C/P ratio in the range 400-600 throughout, which was sufficient to increase the cell dry weight to the desired level, but insufficient to effect substantial growth with suppression of PHA accumulation.

EXAMPLE 3

The procedure of Example 1 was repeated with the modification using crude corn oil as carbon source.

Results

The final cell dry weights, yields of PHA and PHA molecular weights obtained in typical runs are shown in the Table.

Example V mol %	Final Cell Dry Weight g/l	% PHA in Dry Cells	g PHA per g Oil used	PHA Mass (g)	Run Time h	Prop- ionate effic- iency mol %
1 7.4	140	64	0.63	1038	80	11.2
2 8.7	204	67	0.63	1728	65	18.2
3 6.9	162	72	0.69	1289	65	24.0

It is evident that Alcaligenes eutrophus grows actively and accumulates PHA efficiently using rape seed oil or corn oil as carbon source. The phosphate feed during PHA accumulation usefully increases the rate of production of PHA and the efficiency with which propionic acid is converted to valerate repeating units in the PHA. Use of crude corn oil affords a further improvement in propionate efficiency.

CLAIMS

- 1 A process for producing poly-3-hydroxyalkanoate (PHA) which comprises culturing at least one strain of Alcaligenes on a carbon source comprising at least one aliphatic carboxylic acid and/or derivative thereof hydrolysable thereto, said acid or derivative or mixture thereof being of low solubility in pure water, by the steps of:
- (a) providing a body of nutrient medium containing assimilable compounds of nitrogen, phosphorus, sulphur and trace elements, the phosphorus quantity corresponding to the requirement of the intended quantity of bacterial cells to be grown;
 - (b) inoculating the body with viable cells of Alcaligenes;
 - (c) providing in said body a quantity of assimilable carbon compound at least corresponding to the quantity of bacterial cells to be grown;
 - (d) aerobically fermenting the inoculated body while monitoring pH and adjusting it by addition of ammonia and/or alkaline alkali metal compound until cell growth stops or slows substantially;
 - (e) aerobically fermenting the product of step (d) by feeding said low-solubility carbon source while monitoring pH and adjusting it by addition of ammonia and/or alkaline alkali metal compound, until a design quantity of PHA has been produced; and

- (f) recovering PHA from the product of step (e).
- 2 A process according to claim 1 in which the carbon compound provided in step (c) is the same as is to be used in step (e).
 - 3 A process according to claim 1 or claim 2 in which the over-all carbon (as C) to phosphorus (as P) weight ratio in step (d) is typically in the range 40-100, especially 50-80, differing according to the chemical composition of the compound.
 - 4 A process according to any one of the preceding claims in which phosphorus is fed to step (e) at a rate sufficient to permit some bacterial growth but insufficient to permit growth to the exclusion of PHA accumulation.
 - 5 A process according to claim 4 in which the weight ratio of total carbon as (C) to total phosphorus (as P) fed to step (e) is in the range 300 to 600.
 - 6 A process according to claim 4 or claim 5 in which the phosphorus feed is at a steady rate during fermentation and at a fixed proportion of the carbon feed.
 - 7 A process according to any one of the preceding claims in which step (e), and also step (d) if an oily carbon source of low water solubility is used, are carried out preferably with vigorous agitation at least by air-sparging and possibly also mechanically, so as to maximise the active surface area of the oil.
 - 8 A process according to any one of the preceding claims in which the cell dry-weight at the end of step (e) or in the steady state of that step if

operating continuously is in the range 100-400 g/litre.

- 9 A process according to any one of the preceding claims in which the design quantity of PHA corresponds to a PHA content in the range 60-80% w/w on cell dry weight (including PHA).
- 10 A process according to any one of the preceding claims in which, to produce polyhydroxybutyrate/-valerate copolymer (PHBV), there is provided in step (e) a carbon source containing an odd number of carbon atoms as part or all of the aliphatic acid (derivative) or additional thereto, for example propionic acid or n-propyl alcohol.
- 11 A process according to any one of the preceding claims in which the Alcaligenes strain is Alcaligenes eutrophus.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 96/00293

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C12P7/62 //(C12P7/62,C12R1:05)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C12P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 520 405 (ASAHI KASEI KOGYO KABUSHIKI KAISHA) 30 December 1992 cited in the application see p. 3, 10 and claim 1 ---	1-11
X	DATABASE WPI Week 9043 Derwent Publications Ltd., London, GB; AN 90-325620 XP002003618 "Preparation of polyester biopolymer - containing units of 3- and 4-hydroxy-butyrate obtained by culturing bacterial strain of alcaligenes" & JP,A,02 234 683 (MITSUBISHI KASEI CORP) , 17 September 1990 see abstract --- -/--	1-11

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"a" document member of the same patent family

Date of the actual completion of the international search

23 May 1996

Date of mailing of the international search report

0 7. 06. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Douschan, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 96/00293

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>APPL. MICROBIOL. BIOTECHNOL., vol. 31, 1989, pages 168-175, XP002003615 STEINBÜCHEL A. UND SCHLEGEL H.G.: "Excretion of pyruvate by mutants of Alcaligenes eutrophus" see especially the summary ---</p>	1-11
Y	<p>INDUSTRIAL CROPS AND PRODUCTS, no. 1, 1993, pages 157-163, XP002003616 EGGINK G. ET AL: "Oleic acid as a substrate for poly-3-hydroxyalkanoate formation in Alcaligenes eutrophus and Pseudomonas putida" cited in the application see the whole article ---</p>	1-11
Y	<p>J. FERM. BIOENG., vol. 74, no. 5, 1992, pages 288-291, XP002003617 KENJI TANAKA ET AL: "Accumulation of Polyphosphate and Substrate Gas Utilization Efficiency in PHB Accumulation Phase of Autrophic Batch Culture of Alcaligenes eutrophus ATCC17697" see the whole article -----</p>	1-11

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 96/00293

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0520405	30-12-92	JP-A- 5064592	19-03-93
		JP-A- 5276934	26-10-93
		US-A- 5346817	13-09-94

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)